



DESCRIPTION

ADHL-FILL-FAST is a 100% solids, two-component, moisture insensitive grey epoxy adhesive gel.

WHERE TO USE

ADHL-FILL-FAST is designed primarily for concrete repairs as a crack filler prior to the application of high performance epoxy floor coating systems. It is recommended for repairing spalled, scaled, and racked concrete in both vertical and horizontal surfaces.

BENEFITS

- Excellent adhesion properties.
- Very easy to mix and apply
- Cures under cool, damp conditions
- Convenient one to one mixing ratio
- Excellent non-sag properties
- Rapid development of hardness and mechanical strengths
- Adheres to damp surfaces
- Moisture insensitive during the application

MIXING

Premix each component separately before using. Combine 1 part (by volume) of Part A with 1 part (by volume) of Part B. Mix with a low speed drill. Thoroughly blend the material until an even consistency is achieved, periodically scrape down the sides and the bottom of container. Apply as soon as possible as the pot life is limited.

LIMITATIONS

Is not recommended for applications where ambient temperatures are below 10°C (50°F) or for underwater repair.

HANDLING PROPERTIES

Mix Ratio, by Volume	1 part A: 1 part B
Density (Mixed) ...	1.08 kg/litre (9.2 lb./US gal)
Pot Life 100g	15 minutes
Initial Cure	6-8 hours
Recoat	2-3 hours
Full Cure	7 days
Color	Clear

APPLICATION

New concrete must be cured for a minimum of 28 days before applying ADHL-FILL-FAST. The substrate must be above 10°C (50°F) and must be free of all dirt, waxes, previously applied coatings, oil, grease, laitance and any foreign matter that may interfere with the bond of the ADHL-FILL-FAST to the prepared substrate. All concrete surfaces to be treated should be shot blast, or mechanically cleaned for the best results. Steel surfaces should be free of dirt, grease, oil or rust. Blast surface using an angular medium such as aluminum oxide or grit to SSPC-SP10 standard, with a minimum profile of 2.5 mils. Where sand-blasting is not practical, the surface should be degreased and mechanically abraded to reveal continuous bright metal.

COVERAGE

Bonding Adhesive 2.0 m²/L (81.5 ft²/U.S. gal).
CLEAN UP

STORAGE

Store in a heated warehouse. Storage at temperatures below 4.5°C (40°F) may cause the resin to crystallize.

SAFETY PRECAUTIONS

Consult Material Safety Data Sheet (MSDS) for specific instructions.

PACKAGING

7 L (1.9 U.S. gal)

CLEAN UP

Clean all equipment with xylene or acetone before epoxy hardens. Read the Material Safety Data Sheet before using.

SHELF LIFE

Two years if kept in original unopened containers under.

SAFETY PRECAUTION

May cause skin, eye and respiratory tract irritation. Consult Safety Data Sheet for specific instructions.

WARRANTY

The recommendations made and the information here in is the result of accurate laboratory and field tests under controlled conditions. We guarantee that the quality and properties of the materials supplied conform to our standards. Adhesiveslab Products, makes no warranties, expressed or implied, as uses and applications are beyond our control. Adhesiveslab Products. shall not be liable for any injury, loss, or damage (direct or consequential) arising from use or inability to use the products. Before using, the user is urged to pre-test the products in his/her own environment to determine the suitability of the products for their intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Adhesiveslab Product's liability, if any, is limited to a refund of the purchased price or replacement of that portion of the merchandise proven to be defective. Adhesiveslab Products shall have no other liability, including liability for incidental, consequential or resultant damages, however caused, whether due to breach of warranty, negligence, or strict liability.

This warranty may not be modified or extended by representatives of Adhesiveslab Products, its distributors or dealers."